

ATTITUDE LIFE SCIENCE PRODUCTS (PVT.) LIMITED

Gate No. 1083, Village Markal, Taluka Rajgurunagar, Pune 412105

Ph No. : (02135) 662403/662404, Alspl@gmail.com

PRODUCT DATA-SHEET

Material :	PPTF 20%
Colour :	Ebony Black
Grade	ALSPLENE20EBNK

Typical Properties of ALSPLENE20EBNK

Sr. No.	Property	Test Standard	Unit	*Typical Value
1	Specific Gravity	ASTM D 792	NA	1.048
2	MFI @ 230°C/2.16 Kg	ASTM D 1238	gm/10 min.	10.5
3	Tensile strength @ yield	ASTM D 638 M	kg/cm ²	210
4	Elongation @ Yield	ASTM D 638 M	%	8
5	Flexural modulus	ASTM D 790	kg/cm ²	22000
6	Notched Izod Impact	ASTM D 256	kg.cm/cm	8
7	Heat Deflection Temperature	ASTM D 648	°C	120
8	Ash content	ASTM D 5630	%	20.1
9	Color Difference	CIE	dE	0.166

Note : 1) The above test results were obtained from injection moulded samples made as per relevant ASTM Standard
2) Please pre-dry the material at 85 °C for about 2 hour.

Disclaimer:

The above test results are obtained under specific conditions and methods as per standard operating procedure. There is no guarantee that the same results would be reproduced if it is tested elsewhere.

* Typical values with injection moulded specimens, not to be taken as specification